

Code	Description	Size	Colour
20255	Gorilla MS Expanding Foam	500ml	White

1. Description

Gorilla MS Expanding Foam is ready to use one component self-expanding and 100 % isocyanate free foam. Gorilla MS Foam is filled with HCFC- and CFC-free propellants which are not harmful for the ozone layer.

2. Characteristics

- Excellent stability (no shrinkage or post-expansion)
- High filling capacity
- Good adhesion on most materials (except PE/PP & PTFE)
- High insulation value, thermal and acoustic
- Very good bonding properties
- Freon Free (harmless to ozone layer & "greenhouse" effects)
- High thermal and acoustical isolation
- Not UV Stable

3. Technical Data

Basis:	SMX Polymer
Consistency:	Stable foam, thixotropic
Curing System:	Moisture curing
Skin Formation: (FEICA TM1014)	13 minutes
Cutting Time: (FEICA TM1005)	45 minutes
Free Foamed Density: (FEICA TM1019)	Ca. 31 kg/m ³
Insulation Factor: (FEICA TM 1020)	37mW/m.K
Box Yield: (FEICA TM1003)	500ml yields ca. 9 litres of foam
Joint Yield: (FEICA TM1002)	500ml yields ca. 9 litres of foam
Shrinkage after curing: (FEICA TM1004)	<3 %
Expansion after curing: (FEICA TM1004)	<19 %
Compressive Strength: (FEICA TM 1011)	Ca. 6 kPa
Shear Strength: (FEICA TM 1012)	Ca. 23 kPa
Tensile Strength: (FEICA TM 1018)	Ca. 35 kPa
Elongation at Fmax: (FEICA TM 1018)	Ca. 68,9%
Temperature Resistance:	-40°C till +90°C (fully cured)

*This varies according to ambient conditions such as temperature, humidity, substrate etc

H1 insulation R-Value Calculations based on thickness of Gorilla Expanding Foam Range

Product	mW/m. K (TDS)	Thickness mm									
		50	60	70	80	90	100	125	140	200	220
Gorilla PRO Expanding Foam Aerosol	29.70	1.68	2.02	2.36	2.69	3.03	3.37	4.21	4.71	6.73	7.41
Gorilla PRO Expanding Foam "CnF"	32.00	1.56	1.88	2.19	2.50	2.81	3.13	3.91	4.38	6.25	6.88
Gorilla FLEXI Expanding Foam	35.00	1.43	1.71	2.00	2.29	2.57	2.86	3.57	4.00	5.71	6.29
Gorilla SMART Expanding Foam	37.00	1.35	1.62	1.89	2.16	2.43	2.70	3.38	3.78	5.41	5.95
Gorilla MS Foam	37.00	1.35	1.62	1.89	2.16	2.43	2.70	3.38	3.78	5.41	5.95
Gorilla FR Expanding Foam	30.20	1.66	1.99	2.32	2.65	2.98	3.31	4.14	4.64	6.62	7.28
Gorilla FR Expanding Foam Aerosol	34.00	1.47	1.76	2.06	2.35	2.65	2.94	3.68	4.12	5.88	6.47
Gorilla One Shot Foam	35.40	1.41	1.69	1.98	2.26	2.54	2.82	3.53	3.95	5.65	6.21

4. Applications

- Mounting and sealing of windows and doorframes
- Filling of cavities around pipes
- Connecting of isolation materials and roof constructions
- Application of a soundproofing layer on motors
- Improving thermal isolation in cooling systems

5. Packaging

500ml SMART Aerosol canister (net)

6. Shelf Life

24 months in unopened packaging in a dry and cool storage place between 5°C → 25°C. Upright storage is recommended.

7. Application Instructions

Surfaces

Type: Various porous surfaces such as wood, concrete, stone and other materials commonly used in construction.
Not suitable for PE, PP & PTFE

State: Clean, dry, free of grease and loose particles.

Application

Method: Aerosol can, shake thoroughly (at least 20 seconds) before application
Fill holes and cavities for 1/3 (as the foam will expand)
Repeat shaking regularly through application process

Canister temperature: +10°C → +30 °C
Ambient temperature: +5°C → +30 °C
Surface temperature: +5°C → +30 °C

Clean: Gorilla Expanding Foam Cleaner before curing
Repair: Gorilla MS Expanding Foam

Pre-treatment: Moisture in the air or the substrates will cure the adhesive, which will foam slightly. Slightly moistening the substrates will speed up the cure and increase the filling properties of the adhesive. Adhesion to metal batons is determined by surface preparation. An initial wipe with Gorilla 696 Surface Activator is required.

Limitations

- Gorilla MS Expanding Foam can be applied to a wide variety of substrates. Due to the fact that specific substrates may differ from Supplier to Supplier, Soudal recommends preliminary compatibility tests.
- Gorilla MS Expanding Foam is not UV-Resistant.

Remarks:

- Always moisten surfaces in order to improve curing and cellular structure
- Cured MS Expanding Foam must be protected from UV-radiation by painting or applying a top layer of sealants (silicone, MS Polymer, etc)
- For the filling of large volumes apply product in layers and moisten between each layer
- Always store canister with the valve pointed upwards

Soudal recommends preliminary compatibility tests on surfaces on which SMX Foams have not been applied previously.

8. Health and Safety Recommendation

- Apply the usual industrial hygiene.
- Wear gloves and safety goggles.

Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email info@soudal.co.nz.***

Last Updated: 13 June 2022

Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	14 Avalon Drive	Phone: (07) 847 5540
	Nawton	
	Hamilton 3200	Email: sales@soudal.co.nz
	New Zealand	Website: www.soudal.co.nz